

PCTWORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : A61L 25/00, 15/58, C09J 11/08	A1	(11) International Publication Number: WO 98/01167 (43) International Publication Date: 15 January 1998 (15.01.98)
(21) International Application Number: PCT/DK97/00291 (22) International Filing Date: 2 July 1997 (02.07.97) (30) Priority Data: 0772/96 10 July 1996 (10.07.96) DK (71) Applicant (for all designated States except US): COLOPLAST A/S [DK/DK]; Holtedam 1, DK-3050 Humlebaek (DK). (72) Inventor; and (75) Inventor/Applicant (for US only): NIELSEN, Inger, Mann [DK/DK]; Vagtelvej 78, DK-2000 Frederiksberg (DK). (74) Common Representative: COLOPLAST A/S; Patent Dept., Kim Nilausen, Holtedam 1, DK-3050 Humlebaek (DK).		(81) Designated States: AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CU, CZ, DE, DK, EE, ES, FI, GB, GE, HU, IL, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, TJ, TM, TR, TT, UA, UG, US, UZ, VN, YU, ARIPO patent (GH, KE, LS, MW, SD, SZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, ML, MR, NE, SN, TD, TG). Published <i>With international search report.</i>
(54) Title: ADHESIVE AGENT AND USE OF SUCH AGENT (57) Abstract An adhesive agent for application to human or animal skin, preferably for use in connection with ostomy or incontinence appliances, comprises a pressure sensitive adhesive and optionally additives conventionally used in adhesives of this kind and parts of or extracts from Aloe vera. Such adhesive prevents or alleviates skin problems.		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece			TR	Turkey
BG	Bulgaria	HU	Hungary	ML	Mali	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MN	Mongolia	UA	Ukraine
BR	Brazil	IL	Israel	MR	Mauritania	UG	Uganda
BY	Belarus	IS	Iceland	MW	Malawi	US	United States of America
CA	Canada	IT	Italy	MX	Mexico	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NE	Niger	VN	Viet Nam
CG	Congo	KE	Kenya	NL	Netherlands	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NO	Norway	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	NZ	New Zealand		
CM	Cameroon			PL	Poland		
CN	China	KR	Republic of Korea	PT	Portugal		
CU	Cuba	KZ	Kazakstan	RO	Romania		
CZ	Czech Republic	LC	Saint Lucia	RU	Russian Federation		
DE	Germany	LI	Liechtenstein	SD	Sudan		
DK	Denmark	LK	Sri Lanka	SE	Sweden		
EE	Estonia	LR	Liberia	SG	Singapore		

TITLE

Adhesive agent and use of such agent

FIELD OF THE INVENTION

The present invention relates to an adhesive agent for application to human or
5 animal skin, a method of producing such adhesive agent and an adhesive paste
for application to human or animal skin. Furthermore, the invention relates to the
use of the adhesive agent for securing of ostomy appliances and sealing around
an ostomy, for wound dressings, for securing of devices for collecting urine,
wound drainage bandages, orthoses and prostheses and for protection of skin
10 areas and parts of the body against pressure, impacts, friction and/or exudates
from the body, and the use of the adhesive agent as an ostomy paste.

BACKGROUND OF THE INVENTION

Skin adhesive agents are today among other things. used for the above-
mentioned purposes.

15 A widely used embodiment of skin adhesive agents comprises a pressure sensi-
tive adhesive elastomeric matrix in which water absorbing and water-swellable
particles of hydrocolloids are dispersed. The pressure sensitive adhesive matrix
will adhere to skin and contribute to the cohesion of the adhesive. The water ab-
sorbing properties of the hydrocolloids enable adhesion to moist skin by remov-
20 ing moisture from the surface. As the hydrocolloids constantly absorb moisture
emanating from the skin or originating from exuding wounds or from e.g. a
stoma, the hydrocolloids also contribute to the securing a good adherence over
extended periods of time and also prevent maceration of the skin.

In the fields of use mentioned above, the adhesive agents will come into contact
25 with body fluids of different kinds: faeces, urine, wound exudates, sweat *et cetera*. Existing skin adhesives often suffer from the drawback that the adhesive-
ness is destroyed by contact with body fluids. The parts of the adhesive being in
direct contact with the skin or which is exposed to the body fluids will gradually

swell due to the water absorbing and water-swelling properties of the hydrocolloids which will eventually cause a disintegration of the adhesive matrix .

Skin problems are common for persons having a stoma. Generally, about 40 % have skin problems (Pearl et al. 1985 "Early local complications from intestinal
5 stomas", Arch. Surg. 120; 1145-1147.) and the frequency is especially high for persons having an urostomy or ileostomy. About 80 % of the persons having an ileostomy have skin problems (Hellman, J.D., Lago, C.P. 1990 "Dermatologic complications in colostomy and ileostomy patients", International Journal of Dermatology, 29 (2); 129-133.). The skin problems are mostly pronounced in a circula
10 lar area around the stoma ($\frac{1}{2}$ inch from the stoma) (Hellman and Lago 1990).

Two common causes for skin problems are

- Inflammatory changes caused by cronical irritation
- Infection by bacteria and/or fungi.

Skin problems associated with an ostomy are differing from skin problems generally associated with adhesives for skin (dressings or plasters) as the adhesives
15 of ostomy appliances are placed permanently at the same site during long periods of time (cronical irritation) whereas other adhesives for skin are normally only placed at the same site for a short period of time.

It is desirable that the adhesives for use in connection with ostomy appliances
20 are formulated so as to minimise the risk of skin problems and even more desirable if the adhesive might directly alleviate skin problems which have occurred.

During use in ostomy appliances it is observed that the adhesive agent around the stoma is often gradually eroded due to the disintegration of the adhesive giving access to the skin for the exudates. This is particularly a problem for ostomy
25 patients having a urostomy or an ileostomy from which the exudates are fluid and aggressive. The result is that the risk of leakage increases as will the risk of direct contact between exudate and skin which may lead to severe skin problems

and the ostomy appliance and with this, the adhesive will have to be changed more frequently than desired which again will stress the skin and cause higher expenses.

If the adhesive has been extensively eroded by aggressive exudates, the changing of the adhesive appliance may be rendered more inconvenient and laborious as left eroded adhesive will have to be removed mechanically which may cause further stress and strain to the skin. If optional remnants of adhesive are not removed entirely, they may hamper the adhering of the substitute appliance.

Similar problems may be encountered when using adhesive agents for wound drainage bandages or for bandages for use with cronical wounds or especially exuding wounds.

When bandaging wounds, contact between the adhesive and wound exudate will have a similar disintegrating effect on the adhesive leading to problems of the same kind as discussed above when changing the bandage, and furthermore, left parts of adhesive in the wound may affect the wound-healing process. In case of leakage, a further risk of contamination and microbial infection of the wound exists.

Adhesive agents are also used for securing devices such as uridomas for collecting urine from incontinent males. In such an application, a similar risk of disintegration of the adhesive due to direct contact with urine exists and the direct contact between urine and skin may lead to similar problems as discussed above.

Adhesive agents are also used for securing orthoses and prostheses, e.g. breast prostheses, and for protection of skin areas or parts of the body against pressure, impacts and/or friction. In these applications secretion of sweat will be the primary cause for swelling and disintegration of the adhesive agent and irritation

of the skin leading to the inconveniences and problems mentioned above in connection with exchange of the appliance.

Typical examples of adhesives used as skin adhesives are the hydrocolloid adhesives disclosed in DK patent specifications Nos. 147,034 and 147,035 and in
5 US patent specification No. 4,551,490.

Adhesive pastes are especially used for filling cavities or irregularities in the skin around e.g. an ostomy in order to obtain a plane surface for adhesion of the adhesive for securing an ostomy appliance and for sealing between the adhesive agent and an ostomy. A paste is normally of a semi-liquid, more plastic consistency and may e.g. be based on a solution of a film forming polymer in which hydrocolloid particles are dispersed in an alcohol such as ethanol. Agents
10 conventionally used for enhancing the adhesiveness may also be added. Such an adhesive agent may further comprise agents for regulating the viscosity and/or stabilisers and/or preservatives and such adhesives suffer from the same
15 drawbacks as mentioned above.

Typical examples of the composition of adhesive agents are disclosed in DK patent specification No. 155,571 and EP patent specification No. 48,556.

Thus, there is still a need for an adhesive agent or paste having improved performance with respect to alleviating the skin problems caused by the action of
20 aggressive exudates or excretions from a body.

BRIEF DESCRIPTION OF THE INVENTION

It has surprisingly been found that when adding Aloe vera to an adhesive agent for use in appliances to be used in connection with collection of exudates or excretions from a body, a better protection of the skin against the aggressive action
25 of excretions from the body is achieved.

Thus, the invention relates, in its broadest aspect to an adhesive agent for application to human or animal skin comprising a pressure sensitive adhesive and optionally additives conventionally used in adhesives of this kind which adhesive agent comprises Aloe vera.

5 Furthermore, the invention relates to a method of producing such adhesive agent, and an adhesive paste for application to human or animal skin, to the use of such adhesive agent for securing of ostomy appliances and sealing around an ostomy, for wound dressings, for securing of devices for collecting urine, wound drainage bandages, orthoses and prostheses and for protection of skin areas
10 and parts of the body against pressure, impacts, and friction, and /or exudates from the body and the use of the adhesive paste as an ostomy paste.

DETAILED DESCRIPTION OF THE INVENTION

The present invention relates to an adhesive agent for application to human or animal skin comprising a pressure sensitive adhesive and optionally additives
15 conventionally used in adhesives of this kind which adhesive agent is characterised in that it comprises parts of or extracts from Aloe vera.

The basic idea is to add Aloe vera powder (prepared from Aloe vera gel) directly to the adhesive as a component which surprisingly has been found to prevent and alleviate skin problems for users of ostomy appliances.

20 When the adhesive absorbs moisture in the form of sweat, secretion from a stoma or a wound or a crack, or urine flowing into an uridoma, it swells and the Aloe vera components being soluble in water are released. In the area next to a stoma or an exuding wound the adhesive may be moistened to a considerable extent due to secretions from the stoma or wound and thus, Aloe vera will especially be released in the area next to the stoma or wound, exactly at the site having the most pronounced skin problems (Hellman and Lago 1990).
25

It is advantageous to add the Aloe vera as a component of the adhesive instead of applying an Aloe vera gel directly to the skin for the following reasons:

It saves an operation, it is not necessary to await the evaporation of the water of an Aloe vera gel before placing the ostomy appliance or wound dressing (if the skin is not completely dry when placing the appliance, the adhesive will not obtain good adhesion to the skin), a reduction of the adhesion of the adhesive agent to the skin due to the presence of Aloe vera components on the skin is avoided, and a controlled release of Aloe vera from the adhesive is obtained giving the highest release in the most humid areas next to the stoma or wound where most of the skin problems occur.

Aloe vera is reported to have an antibacterial effect (Grindlay, D., Reynolds, T. 1986 "The Aloe vera phenomenon: A review of the properties and modern uses of the leaf parenchyma gel", Journal of Ethnopharmacology, 16; 117-151) and furthermore to have an anti-inflammatory effect (Davis, R.H., Rosenthal, K.Y., Cesario, L.R., Rouw, G.A. 1989 "Processed Aloe vera administered topical inhibits inflammation", Journal of the American Podiatric Medical Association, 79 (8); 395-397).

Nearly 200 species of Aloe exist. Only few of these do have commercial interest, amongst these Aloe vera (= A. Barbadensis). Aloe vera is a perennial plant having sturdy leaves of a weight of up to half a kilogram containing clear gel (colourless mucilaginous pulp) consisting of about 99.5% water.

The Aloe vera is commercially available in the form of a gel and in the form of a spray dried or freeze dried powder (dried gel) in various concentrations. Of most interest for the adhesives of the invention is Aloe vera gel in powder form as it may be mixed directly into the adhesive.

The natural gel comprises about 0.5% Aloe vera solids. A spray dried powder has a concentration 100x higher than the gel and a freeze dried powder a concentration 200x the concentration of the gel. Thus, freeze dried Aloe vera powder is 200 times as concentrated as the gel. Spray dried Aloe vera powder is

"only" 100 times as concentrated as the natural gel because this powder comprises a carrier, typically malto-dextrin.

Japanese patent publication No. 4-54107 discloses a cosmetic product comprising an adhesive containing an Aloe extract and polyvinylpyrrolidone and/or a co-
5 polymer containing polyvinylpyrrolidone and a second component composed of a polymer or copolymer of acrylic acid and/or methacrylic acid which product is stated not to give harmful irritation to the skin.

Japanese patent publication No. 4-54108 discloses a cosmetic product comprising a plastic film and an adhesive containing an Aloe extract and polyvinylpyr-
10 rolidone and/or a copolymer containing polyvinylpyrrolidone and a second component comprising a low-molecular weight polyhydric alcohol having < 2000 molecular weight which product is stated not to give harmful irritation to the skin.

Japanese patent publication No. 6-65073 discloses a water proof adhesive plas-
15 ter having a waterproof backing and an adhesive layer comprising pharmaceutical, e.g. D,L-alpha-tocopherol, moistening the skin and giving continuous action of the drug component. The tacky adhesive layer contains a tacky adhesive and at least one kind of drug selected from dl-alpha-tocopherol acetate, retinol acetate, retinol palmitate, biotin, panthothenic acid, olive oil, Aloe and rice bran.

20 Japanese patent publication No. 4-283511 discloses a two component skin plaster with durable adhesion and cooling sensation comprising a composition containing hydrogel and composition comprising water-soluble powdery substance. An aloe extract may be applied to the plaster.

US patent specifications Nos. 4,917,890, 4,959,214 and 4,966,892 as well as
25 EP patent specifications Nos. 227,806 and 328,775 is disclosed gels containing an extract of Aloe vera and Carbopol® 940 for use in healing of wounds.

However, there is no indication nor suggestion to add Aloe vera to a hydrocolloid adhesive for use in ostomy or incontinence appliances or a wound dressing nor indication or suggestion that such addition should impart a better protection of the skin against the aggressive action of excretions from the body. Now it has
5 surprisingly been found that an improved performance is obtained using adhesives comprising Aloe vera and a hydrocolloid.

Ostomy appliances comprising an adhesive according to the invention may be any appliance known per se, the difference being use of the adhesive of the invention. The appliances may be one-piece or two-piece appliances. Incontinence
10 appliances comprising an adhesive according to the invention may be any appliance known per se, e.g. an urisheet or uridom. The adhesive may be placed directly on the sheeth or on a separate adhesive strip for securing the urisheet to the penis. Wound dressings comprising an adhesive according to the invention may be any appliance known per se, e.g. wound dressings for cronic ulcers which
15 may be in the form of larger plates or in the form of minor dressings adapted for treatment or prevention of cracks or fissures, callus or corns, or ablations.

The adhesive of the invention preferably comprises a plastic or elastomeric matrix having hydrocolloid particles dispersed therein.

The elastomeric matrix may e.g. be based on polyisobutylene, butyl gum, styrene
20 blockcopolymers, polyacrylates or acrylate copolymers, silicone gum, natural gum, polyurethane gum, polyvinylether and mixtures thereof.

Additives conventionally used in additives for ostomy or incontinence appliances or wound dressings are e.g. additives for adjusting self-adhesive and cohesive properties of the matrix. Thus, it may be supplied with substances for promoting
25 the adhesiveness, e.g. a resin, or emulsifiers, e.g. an oil, and/or antioxidants for protecting an elastomer against degradation or decomposition. Such additives are well-known within the art and are e.g. described in US patent No. 4,551,490 and in DK patent No. 147,035.

In accordance with one embodiment of the invention the adhesive matrix comprises a polyisobutylene and a hydrocolloid.

Such an adhesive typically comprises from 25 to 50% (w/w) polyisobutylene, from 0 to 20% (w/w) butyl rubber, from 0 to 15% (w/w) tackifying resin and from
5 25 to 55% (w/w) of hydrocolloid.

In accordance with another embodiment of the invention the adhesive matrix comprises a blockcopolymer comprising styrene and one or more olefins and/or dienes, e.g. olefins or dienes having 4 - 6 carbon atoms, preferably having 4 carbon atoms, such as 1-butene, isoprene or butadiene. The blockcopolymer may
10 e.g. be a styrene-isoprene copolymer or a styrene-butadiene-styrene copolymer.

Typically such an adhesive comprises from 5 to 30% (w/w) styrene-isoprene-styrene blockcopolymer, from 15 to 50% (w/w) tackifying resin and from 25 to 55% (w/w) of hydrocolloid, and from 0 to 25% (w/w) of plasticizer.

A plasticizer may be any conventional plasticizer for use together with the co-
15 polymer e.g. be a phthalate such as dioctyl phthalate or an adipate such as dioctyl adipate or an oil such as liquid paraffin.

The amount of Aloe vera present in the adhesive of the invention may be from 0.01 to 5% (w/w) which ensures a pain relieving effect, an enhancing effect on the healing of a wound, shows a marked antimicrobial activity and shows an anti-
20 inflammatory effect.

The amount of Aloe vera is preferably from 0.3 to 3% (w/w).

Suitable hydrocolloids for use in such adhesives are naturally occurring hydrocolloids such as guar gum, locust bean gum, pectin, alginates, gelatine, xanthan or karaya gum, semisynthetic hydrocolloids such as cellulose derivatives, e.g. salts
25 of carboxymethylcellulose, methylcellulose and hydroxypropylmethylcellulose,

sodium starch glycollate and synthetic hydrocolloids such as polyvinyl pyrrolidone, polyvinyl alcohol, polyethylene glycol or certain polyacrylates. The hydrocolloid may be wholly or partly be constituted by psyllium material as disclosed in WO 96/00094.

- 5 The invention also relates to a method of producing an adhesive agent for application to human or animal skin, preferably for use in connection with ostomy or incontinence appliances comprising a pressure sensitive adhesive and optionally additives conventionally used in adhesives of this kind, said adhesive agent comprises parts of or extracts from Aloe vera which method comprises mixing, in a
10 heated mixer, a plastic or elastic matrix-forming adhesive material and a part of a hydrocolloid material, turning off the heating, continuing the mixing for a short while, admixing the remaining part of the hydrocolloid material and Aloe vera and continuing the mixing *in vacuo* up to a homogeneous mixture is obtained.

- The invention further relates to a paste for application to human or animal skin,
15 which paste comprises an adhesive agent for application to human or animal skin, preferably for use in connection with ostomy or incontinence appliances comprising a pressure sensitive adhesive and optionally additives conventionally used in adhesives of this kind, said adhesive agent comprises parts of or extracts from Aloe vera.

- 20 In another aspect, the invention relates to the use of an adhesive agent comprising Aloe vera and a hydrocolloid for securing ostomy appliances to the skin and for sealing around an ostomy, for securing wound dressings or wound drainage bandages to the skin, for securing devices for collecting urine to the skin, or for securing orthoses or prostheses to the skin.

- 25 Preferably an adhesive agent comprising Aloe vera is used for securing of an ostomy appliances and sealing around an ostomy, for securing and sealing of devices for collecting urine or for securing orthoses and prostheses, preferably prostheses such as breast prostheses.

In a further aspect the invention relates to the use of an adhesive agent comprising Aloe vera for protection of skin areas and parts of the body against pressure, impacts and friction and/or the aggressive action of excretions from the body.

In accordance with yet another aspect, the invention relates to the use of an adhesive agent comprising Aloe vera as an ostomy paste.

The invention is illustrated more in detail in the below examples which are provided to illustrate presently contemplated preferred embodiments and the best mode for practising the invention, but are not intended to be limiting thereof.

10 MATERIALS AND METHODS

Polyisobutylene: Vistanex® LM-MH from Exxon Chemical

Sodium carboxymethylcellulose (CMC): Blanose® 9H4XF from Hercules

Freeze dried Aloe vera powder: C.E. Roeper

EXPERIMENTAL PART

15 EXAMPLE 1

Preparation of adhesive agent according to the invention

Adhesive agent No. 1

An adhesive agent according to the invention was prepared comprising 40 % by weight of polyisobutylene, 20 % Gelatine, 20 % CMC, 19 % Pectin and 1 %

20 freeze dried Aloe vera powder.

The adhesive was prepared in a Z-blade mixer. Before the mixing, the mixing chamber was heated to 80 °C by means of an oil heater. Polyisobutylene, Aloe vera powder and the hydrocolloids were weighed out separately. Firstly, half the amount of hydrocolloids and all the polyisobutylene were placed in the mixing
25 chamber. The heat supply was turned off. Mixing took place for 1-2 minutes after which the remaining amount of hydrocolloids and the Aloe vera powder were added. Then the mixing was continued in vacuo until a total mixing time of 30

minutes. The adhesive agent was removed from the mixer and pressed into 1 mm thin plates between two sheets of silicon paper in a hydraulic press at 90°C. This adhesive agent was designated adhesive agent No. 1.

Preparation of adhesive agent without Aloe vera for comparison

5 Adhesive agent No. 2

An adhesive agent No. 2 was manufactured in a similar manner. This is a standard recipe for an ostomy adhesive agent and is directly comparable to adhesive agent no. 1, except for freeze dried Aloe vera powder.

Comparison of adhesive agent no. 1 and 2.

10 Standard laboratory tests have been carried out.

Tack test

In the tack test a Teflon probe of defined surface roughness ($R_a = 0.5$) and area (6 mm diameter) is brought into contact with the adhesive at a controlled rate (50 mm/min), under a fixed pressure (3N) for a short time (2 seconds) and subsequently the bond formed between the probe and adhesive is broken, also at a controlled rate (500 mm/min). Tack is measured as the maximum force required in breaking the adhesive bond.

Peel test

The peel adhesion is defined as the force required to remove the adhesive, which has been applied to a standard test plate (Teflon, $R_a = 2$) under specified conditions (23°C and 50 %RH) from the plate at a specified angle (90°) and speed (300 mm/min). The peel adhesion is measured 30 minutes after application of the adhesive to the test plate. The adhesive strips are 20 mm wide and have a minimum length of 175 mm in the machine direction. Peel adhesion is expressed in Newton per 20 mm.

Water absorption

Water absorption involves soaking adhesive strips into a 0.9% aqueous solution of sodium chloride under specified conditions (37°C). Only one side of the adhesive is exposed to the aqueous solution. The absorption is calculated as the weight gain of the adhesive per square centimetre.

Table 1. Laboratory test results.

Adhesive agent No.	Composition	Amount (Wt. %)	Tack (N)	Peel (N)	Water abs. (g/cm ²)
1	Polyisobutylene	40	15	10	0
	Gelatine	20			
	Pectin	19			
	CMC	20			
	Freeze dried Aloe vera	1			
2	Polyisobutylene	40	14	10	0
	Gelatine	20			
	Pectin	20			
	CMC	20			

As can be seen from Table 1, the laboratory test results are similar for adhesive agent no. 1 and 2. This means, that freeze dried Aloe vera powder added in an amount of 1 % does not have any adverse effect on the adhesive properties.

10 EXAMPLE 2

Preparation of adhesive agents according to the invention

Adhesive agent No. 3

Adhesive agent No. 3 was manufactured in a similar manner as agent No. 1. The composition is stated in Table 2 below. Psyllium is a term for a water-absorbing, mucus forming material which is produced from the seeds from plants of the genus *Plantago*.

Adhesive agent No. 4

Adhesive agent No. 4 was manufactured in a similar manner as agent No. 1. The composition is stated in Table 2 below.

Preparation of adhesive agent without Aloe vera for comparison

Adhesive agent No. 5

Adhesive agent No. 5 was manufactured in a similar manner as agent No. 1. The composition is stated in Table 2 below.

5 Comparison of adhesive agent Nos. 3, 4 and 5.

Testing of the time until first appearance of microbial contamination

The adhesive was placed in a moist atmosphere (100 %RH) at 40°C. One side of the adhesive was uncovered and is thereby exposed to the moist atmosphere.

The time until the first appearance of microbial contamination was determined by
10 visual inspection of the exposed surface.

Table 2. Laboratory test results.

Adhesive agent No.	Composition	Amount (Wt. %)	Time until first microbial appearance
3	Polyisobutylene Psyllium Freeze dried Aloe vera	40 59 1	~ 48 hours
4	Polyisobutylene Psyllium Freeze dried Aloe vera	40 59.5 0.5	~ 35 hours
5	Polyisobutylene Psyllium	40 60	less than 24 hours

It appears from Table 2 that Aloe vera has an anti-microbial effect in an adhesive according to the invention and that the effect is increasing with increasing concentration of Aloe vera. The anti-microbial effect is present after manufacturing the adhesive, which means that the heat used for the mixing of the adhesive
15 is not destroying the active components in Aloe vera.

CLAIMS

1. An adhesive agent for application to human or animal skin, preferably for use in connection with ostomy or incontinence appliances comprising a pressure sensitive adhesive and optionally additives conventionally used in adhesives of this
5 kind, c h a r a c t e r i s e d in that the adhesive agent comprises parts of or extracts from Aloe vera.
2. An adhesive agent as claimed in claim 1 wherein the pressure sensitive adhesive comprises a plastic or elastomeric matrix having hydrocolloid particles dispersed therein.
- 10 3. An adhesive agent as claimed in claim 2 wherein the matrix comprises a polyisobutylene.
4. An adhesive as claimed in claim 2 or 3 comprising from 25 to 50% (w/w) polyisobutylene, from 0 to 20% (w/w) butyl rubber, from 0 to 15% (w/w) tackifying resin and from 25 to 55% (w/w) of hydrocolloid.
- 15 5. An adhesive agent as claimed in claim 2 wherein the matrix comprises a blockcopolymer comprising styrene and one or more olefins and/or dienes.
6. An adhesive agent as claimed in claim 5 wherein the matrix comprises a styrene-isoprene-styrene copolymer.
7. An adhesive as claimed in claim 2 or 3 comprising from 5 to 30% (w/w)
20 styrene-isoprene-styrene copolymer, from 15 to 50% (w/w) tackifying resin and from 25 to 55% (w/w) of hydrocolloid and from 0 to 25% (w/w) of plasticizer.
8. An adhesive as claimed in any of claims 1 - 7 wherein the contents of Aloe vera is from 0.01 to 5% (w/w).

9. An adhesive as claimed in claim 8 wherein the contents of Aloe vera is from 0.3 to 3% (w/w).

10 A method of producing an adhesive agent for application to human or animal skin, preferably for use in connection with ostomy, incontinence or wound care
5 appliances comprising a pressure sensitive adhesive and optionally additives conventionally used in adhesives of this kind, said adhesive agent comprises parts of or extracts from Aloe vera which method comprises mixing, in a heated mixer, a plastic or elastic matrix-forming adhesive material and a part of a hydro-
colloid material, turning off the heating, continuing the mixing for a short while,
10 admixing the remaining part of the hydrocolloid material and Aloe vera and continuing the mixing *in vacuo* up to a homogeneous mixture is obtained.

11. Use of an adhesive agent comprising Aloe vera and a hydrocolloid for securing ostomy appliances to the skin and for sealing around an ostomy, for securing wound dressings or wound drainage bandages to the skin, for securing devices
15 for collecting urine to the skin, or for securing orthoses or prostheses to the skin..

INTERNATIONAL SEARCH REPORT

International application No.

PCT/DK 97/00291

A. CLASSIFICATION OF SUBJECT MATTER

IPC6: A61L 25/00, A61L 15/58, C09J 11/08

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC6: C09J, A61L

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

SE,DK,FI,NO classes as above

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	WO 9600094 A1 (COLOPLAST A/S), 4 January 1996 (04.01.96), abstract, claims --	1-7, 11
A	File WPI, Derwent accession no. 94-121171, SEKISUI CHEM IND CO LTD: "Waterproof adhesive plaster giving pharmaceutical effect - has waterproof backing and adhesive layer contg pharmaceuticals e.g. D,L-alpha-tocopherol"; & JP,A,6065073, 940308, DW9415 --	1-8
A	US 5420114 A (PERCY B. CLODMAN ET AL), 30 May 1995 (30.05.95), claims 5, 9 --	1,8-9

☒ Further documents are listed in the continuation of Box C.☒ See patent family annex.

* Special categories of cited documents:

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier document but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance: the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance: the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art

"&" document member of the same patent family

Date of the actual completion of the international search

15 October 1997

Date of mailing of the international search report

20.10.97

Name and mailing address of the ISA/
Swedish Patent Office
Box 5055, S-102 42 STOCKHOLM
Facsimile No. +46 8 666 02 86

Authorized officer

Sofia Nikolopoulou
Telephone No. +46 8 782 25 00

INTERNATIONAL SEARCH REPORT

International application No.

PCT/DK 97/00291

C (Continuation). DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	WO 8910750 A1 (BUSCIGLIO, JOHN, A.), 16 November 1989 (16.11.89), abstract, claims ----- -----	1,8

INTERNATIONAL SEARCH REPORT

Information on patent family members

International application No.

PCT/DK 97/00291

Patent document cited in search report			Publication date	Patent family member(s)			Publication date
WO	9600094	A1	04/01/96	AU	2785295	A	19/01/96
				DK	75994	A	25/12/95

US	5420114	A	30/05/95	CA	2126704	A	08/01/95
				US	5498603	A	12/03/96

WO	8910750	A1	16/11/89	CA	1320909	A	03/08/93
				US	4748022	A	31/05/88
